Körabond HG 73



Primer for the pre-treatment of coated surfaces, glass, ceramics and stainless steel as basis for subsequent bonding

TECHNICAL DATA

Base	Synthetic re	Synthetic resin, containing solvents			
Colour	Colourless	Colourless up to slightly yellowish, transparent			
Consistency	Liquid				
Density	0.8	g/cm³			
Consumption	20-80	g/m²			

PROCESSING

Processing temperature

+10°C to +25°C

Preparation

The surfaces to be primed need to be dry, clean and free of dust and grease.

Apply a thin layer of **Körabond HG 73** to the surfaces to be bonded and allow to dry. Drying time is about 10 minutes. The subsequent bonding should be carried out after 24 hours

at the latest. In case of unknown or new materials, prior testing with regard to suitability and compatibility is required.

SPECIAL NOTES

Storage

Keep containers tightly closed. Do not store below $+10\,^{\circ}$ C for more than 12 months.

CLEANING

Körasolv GL

SAFETY

Please read our Safety-Data-Sheet and the labels of each product before use.

Pay particular attention to the directions given in the Dangerous Substance Regulations.

Make sure the safety data sheet is readily available as it gives valuable information regarding the safe usage and disposal of the product and what to do in the event of an accident involving the product.

PACKAGING UNITS

5 I can 200 I drum 400 g can (carton à 20 pcs.)

PRODUCT NUMBER

C31001

For safety related data please refer to the safety data sheet!

Please note: All given data are based on careful examination in our laboratories and our past practical experience. These are non-binding indications. Given the high number of materials appearing on the market and the different methods of use which are beyond our influence and control, we naturally cannot accept any responsibility for the results of your work, also with regard to third party patent rights. We recommend that sufficiently thorough tests be carried out to as certain whether the product described will meet the requirements of your particular case. Please also note our Terms of Sale, Delivery and Payment. This product information replaces all previous issues.



Zweibrücker Str. 200 D-66954 Pirmasens Phone +49 6331 56-2000 Fax +49 6331 56-1999 eMail Internet

info@koe-chemie.de www.koe-chemie.de

